

ABSTRACT OF THE DISCLOSURE

A method of dry etching a magnetic material which is capable of precise etching of fine etching target areas of a magnetic material with target widths of 150 nm or less,
5 wherein the ratio of the flow rate of carbon monoxide gas relative to the total flow rate of reactive gas is within a range from 1% to 40%.